

EP0126341

Biblio Desc Glaims Page 1

Drawing espace















Process for the preparation of esters of (meth)-acrylic acid, and their use.

Patent Number: EP0126341 Publication date: 1984-11-28

Inventor(s): SCHORNICK GUNNAR DR; BUETHE INGOLF DR; JACOBI MANFRED DR;

LENZ WERNER DR; LEHNERER WOLFGANG DR

Applicant(s):: BASF AG (DE)

Requested Patent:

EP0126341, B1

Application

Number:

EP19840104853 19840430

Priority Number

(s):

DE19833316593 19830506

IPC

Classification:

C07C69/54; C07C67/08; C07C67/26; C09D3/80

EC

Classification:

C08F290/06, C08G63/47, C09D4/00, C09D163/00, C09D167/06

Equivalents:

DE3316593

Abstract

1. A process for preparing an ester of acrylic or methacrylic acid with a hydroxyl-containing organic compound, which comprises esterifying a saturated polyester which contains no fewer than 2 free hydroxyl groups per molecule and may contain ether groups or a saturated polyether which contains no fewer than 2 free hydroxyl groups per molecule, this polyester or polyether having an average molecular weight ~Mn of from 400 to 4,000, with from 100 to 150 mol %, based on the OH groups of the polyester or polyether, of acrylic acid or methacrylic acid in the presence of an acidic esterification catalyst and one or more hydrocarbons forming an azeotropic mixture with water and a small amount of a polymerization inhibitor at elevated temperature with azeotropic removal of the resulting water, after the esterification removing the hydrocarbon by distillation and after neutralization of the esterification catalyst reacting the remaining acrylic or methacrylic acid with an amount, equivalent to the acid number, of an epoxy compound having no fewer than two epoxy groups per molecule until an acid number =< 5 mg of KOH/g is obtained.

Data supplied from the esp@cenet database - 12